



Hydracure AR

*Acrylic Base Curing Compound
Meets ASTM C309*

Description

Hydracure AR is suitable for use on fresh or aged, interior or exterior concrete.

Hydracure AR is non-flammable, odorless and non-explosive, so it may be used safely in areas where a petroleum based material might be hazardous.

Hydracure AR is an acrylic emulsion based liquid membrane curing compound, content white pigment. It consists of a stable emulsion based on suitably processed non-toxic emulsion.

Advantage

- Reduces surface shrinkage and cracking by eliminating moisture loss from exposed surfaces
- Enables cement to hydrate more efficiently
- Saves time, can be applied as soon as possible after finishing concrete
- Eliminates need for damp hessian, sand or polyethylene
- Fast-forming film dries within 15-30 minutes depending on ambient temperature and site conditions
- Can be over-coated with specific rendering, painting, etc. Please consult ACT.
- Forms a non-staining continuous white film on clean stain-free concrete or rendered surfaces.

Instruction for Use

Hydracure AR is formulated for easy application by brush, roller or power spray equipment. Best results are obtained by spray application. It is ready to use. Do not dilute, apply a continuous uniform film and allow at least 30 min drying if second coat is required. For heavy traffic, allow for 24 hours drying time.

Coverage

Power Floated	10 m ² / l.
Fine Texture	6.5 to 7.5 m ² / l
Rough Texture	5 to 6.5 m ² / l

Coverage rates may vary due to surface absorption and application.

Characteristics

Appearance:	White
Bulk density:	1.05-1.07
Drying Time :	15-30 min

Packing

20 L. or 210 L.

Storage

Store under dry conditions and in unopened containers, not below 5 °C. Do not expose to strong sunshine. Keep well away from open flames.

Act (Thailand) Co., Ltd.

Address : 19 Moo 1 Kubangluang
Lardlumkaew Pathumthai 12140
Tel. : (66)-0-2979-4446-9 , (66)-0-29794936-9
Fax. : (66)-0-2979-4445
Email : info@actthai.com
Web Site : <http://www.actthai.com>

Non-warranty. The information contained herein is believed to be reliable to the best of our knowledge. However, all recommendations are made without guarantee of performance and with warranty of freedom from legal responsibility including patent liability on the part of Act (Thailand) Co., Ltd